

High Voltage Chips Capacitors

C Series

According to
Available space ranges:
consult our detail
specifications



FEATURES

- Multilayer chip ceramic capacitors
- Size 1515 to 16080
- NPO, C4xx and X7R dielectrics
- Capacitance range: 10pf to 39 μ F
- Voltage range: 200 V_{DC} to 10,000 V_{DC}

PHYSICAL CHARACTERISTICS

CONSTRUCTION

- C Series: Unleaded chip capacitors for surface mounting with optional tinning.
- P, PL, L models: DIL leaded uncoated chip capacitors for surface mounting recommended to eliminate thermomechanical stresses.
- N, NU models: DIL leaded chip capacitors for through-hole circuits (N: varnished chips, NU: uncoated chips).
- R, RU models: Ribbon leaded chip capacitors for surface mounting (R: varnished chips, RU: uncoated chips) recommended to eliminate thermomechanical stresses.

MARKING (On request on unleaded chips)

Series, capacitance value, tolerance, rated voltage clear or coded, date code.

ELECTRICAL SPECIFICATIONS

| Dielectric | NPO | C4xx | X7R |
|---|--|--|--|
| Dielectric code | 1 | 4 | 2 |
| Maximum ΔC/°C over temperature range without voltage | NA | NA | $\pm 15\%$ |
| Temperature coefficient | $[0 \pm 30]$ ppm/°C | $[-2,200 \pm 500]$ ppm/°C | NA |
| Aging | None | None | $\leq 2.5\%$ per decade hour |
| Operating temperature | -55°C to $+125^\circ\text{C}$ | | |
| Rated voltage (U_{RC}) | 200 V _{DC} to 10,000 V _{DC} | 200 V _{DC} to 5,000 V _{DC} | 200 V _{DC} to 10,000 V _{DC} |
| Dielectric withstanding voltage | 2.5 U _{RC} for U _{RC} \leq 500 V _{DC} | 2 U _{RC} for U _{RC} = 200 V _{DC} 2 U _{RC} for U _{RC} = 500 V _{DC} | 2.5 U _{RC} for U _{RC} = 200 V _{DC} 2 U _{RC} for U _{RC} = 500 V _{DC} |
| | 1.6 U _{RC} for U _{RC} \geq 1,000 V _{DC} | 1.5 U _{RC} for U _{RC} = 1,000 V _{DC} | 1.5 U _{RC} for U _{RC} = 1,000 V _{DC} |
| | Extended range: 2 U _{RC} for U _{RC} \leq 500 V _{DC} 1.3 U _{RC} for U _{RC} \geq 1,000 V _{DC} | Extended range: 1.4 U _{RC} for U _{RC} $>$ 1,000 V _{DC} | Extended range: 1.2 U _{RC} for U _{RC} $>$ 1,000 V _{DC} |
| | | Extended range: 1.5 U _{RC} for U _{RC} \leq 500 V _{DC} 1.2 U _{RC} for U _{RC} \geq 1,000 V _{DC} | Extended range: 1.5 U _{RC} for U _{RC} \leq 500 V _{DC} 1.2 U _{RC} for U _{RC} \geq 1,000 V _{DC} |
| Capacitance | at 1MHz for C \leq 1,000pf at 1kHz for C $>$ 1,000pf | at 1kHz | at 1kHz |
| | $\leq 0.015 (150/C + 7)\%$ at 1MHz for C \leq 50pf | | |
| Dissipation factor | $\leq 0.15\%$ at 1MHz for 50pf $<$ C \leq 1,000pf $\leq 0.15\%$ at 1kHz for C $>$ 1,000pf | $\leq 0.10\%$ at 1kHz | $\leq 2.5\%$ at 1kHz |
| Insulation resistance at 25°C under U_{RC} for U_{RC} \leq 500V_{DC} under 500V_{DC} for U_{RC} $>$ 500V_{DC} | $\geq 100,000 \text{ M}\Omega$ for C $\leq 10\text{nf}$ $\geq 1,000 \text{ M}\Omega \cdot \mu\text{F}$ for C $> 10\text{nf}$ | $\geq 20,000 \text{ M}\Omega$ for C $\leq 25\text{nf}$ $\geq 500 \text{ M}\Omega \cdot \mu\text{F}$ for C $> 25\text{nf}$ | |


HIGH VOLTAGE

| C | 2 | 80 | C | P | M | F | 1 μ F | 10% | 200V | S12 | T5 |
|---------------------------------|--------------------------------|-------------------|--|---|--|--|----------------------------|---|---|--|--|
| Series | Dielectric | Exxelia size code | Termination (Bare chips only) | Leads style + finishing (Leaded chips only) | Marking | Quality level | Capacitance | Tolerance | Rated voltage | Packaging | Reliability level |
| C = High voltage chip capacitor | 1 = NPO 2 = X7R 4 = C4xx | 78 = 1515 | W = RoHS compliant For all sizes - Ag/Pd/Pt W Ag/Pd/Pt Q wAg QW Ag From 1812 to 3333 sizes - Ag/Pd/Pt W Ag/Pd/Pt H Ag/Pd/Pt + dipped Sn/Pb 60/40 HW Ag/Pd/Pt + dipped Sn E Ni* + dipped Sn/Pb 60/40 C Ni** + electrolytic Sn/Pb 95/5 CW Ni + electrolytic Sn D Ag + Ni*** + electrolytic Sn/Pb 60/40 G Ni + electrolytic Gold From 1812 to 4040 sizes YC Ag + Polymer + Ni + Sn/Pb 95/5 YCW Ag + Polymer + Ni + Sn YD Ag + Polymer + Ni + Sn/Pb 60/40 YG Ag + Polymer + Ni + Au YGW Ag + Polymer + Ni + Au * Only 2225 to 16080 sizes ** Only 1515 to 2220 sizes (other sizes on demand) *** Only 1515 (other sizes on demand) | P PW - RoHS PL PLW - RoHS L LW - RoHS R RW - RoHS RU RUW - RoHS N NW - RoHS NU NUW - RoHS not available for sizes 1515 and 1812 | Only for unleaded chips [Leaded chips are always marked]. - = no marking M = Marking: For sizes 1515 - 1825: Cap. value. For other sizes: EFD, Series, cap. value, tolerance, rated voltage, date code. | - = standard quality level F = Hi-Rel quality: screening in accordance with Exxelia specification | Capacitance value in clear | For NPO dielectric: $\pm 1\%$ $\pm 2\%$ $\pm 5\%$ $\pm 10\%$ $\pm 20\%$ For C4xx dielectric: $\pm 2\%$ $\pm 5\%$ $\pm 10\%$ $\pm 20\%$ For X7R dielectric: $\pm 10\%$ $\pm 20\%$ | 200V 500V 1,000V 1,500V 2,000V 3,000V 4,000V 5,000V 7,500V 10,000V Intermediary and higher voltages available on request. | - = Exxelia packaging (leaded chips: thermoformed packaging) Only available for unleaded chips: S12 = Super 12 reel Sizes 1515 - 2220: BA = Tray package (non oriented chips) BA0 = Tray package (oriented chips) See page 13 | For F parts only. Acc. to Exxelia spec. - T5 T6 See page 15 |

C Series

High Voltage Chips Capacitors

DIMENSIONS in inches (mm)



STANDARD RATINGS

| | Size | 1515 | 1812 | 1825 | 2220 | 2225 | 2825 | 3333 | | | | | | | | | | | | | | |
|----------------------------------|-------------------|------------------------------|------------------------------|-------------------------------|--|--|--|--|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|-------|
| | Exxelia size code | 78 | 79 | 90 | 80 | 91 | 81 | 82 | | | | | | | | | | | | | | |
| Dimensions inches (mm) | L* | 0.15 ± 0.015 (3.8 ± 0.38) | 0.177 ± 0.020 (4.5 ± 0.5) | 0.177 ± 0.020 (4.5 ± 0.5) | 0.224 ± 0.020 (5.7 ± 0.5) | 0.224 ± 0.020 (5.7 ± 0.5) | 0.276 ± 0.020 (7 ± 0.5) | 0.331 ± 0.020 (8.4 ± 0.5) | | | | | | | | | | | | | | |
| | W* | 0.15 ± 0.015 (3.8 ± 0.38) | 0.126 ± 0.020 (3.2 ± 0.5) | 0.250 ± 0.020 (6.35 ± 0.5) | 0.197 ± 0.020 (5.0 ± 0.5) | 0.250 ± 0.020 (6.35 ± 0.5) | 0.250 ± 0.020 (6.35 ± 0.5) | 0.331 ± 0.020 (8.4 ± 0.5) | | | | | | | | | | | | | | |
| | a | 0.012 min (0.3 min) | 0.024 ± 0.020 (0.6 ± 0.5) | 0.024 ± 0.020 (0.6 ± 0.5) | 0.028 ± 0.020 (0.7 ± 0.5) | 0.028 ± 0.020 (0.7 ± 0.5) | 0.039 ± 0.020 (1 ± 0.5) | 0.039 ± 0.020 (1 ± 0.5) | | | | | | | | | | | | | | |
| | d | - | - | 0.087 ± 0.008 (2.2 ± 0.2) | 0.087 ± 0.008 (2.2 ± 0.2) | 0.087 ± 0.008 (2.2 ± 0.2) | 0.087 ± 0.008 (2.2 ± 0.2) | 0.138 ± 0.008 (3.5 ± 0.2) | | | | | | | | | | | | | | |
| | b | - | - | 0.197 ± 0.020 (5 ± 0.5) | 0.197 ± 0.020 (5 ± 0.5) | 0.197 ± 0.020 (5 ± 0.5) | 0.197 ± 0.020 (5 ± 0.5) | 0.315 ± 0.020 (8 ± 0.5) | | | | | | | | | | | | | | |
| | R min. | - | - | 0.066 (1.7) | 0.098 (2.5) | 0.098 (2.5) | 0.137 (3.5) | 0.177 (4.5) | | | | | | | | | | | | | | |
| | C max. | - | - | 0.229 (5.8) | 0.276 (7) | 0.276 (7) | 0.315 (8) | 0.355 (9) | | | | | | | | | | | | | | |
| | X | - | - | 0.2 ± 0.020 (5.08 ± 0.5) | 0.248 ± 0.020 (6.3 ± 0.5) | 0.248 ± 0.020 (6.3 ± 0.5) | 0.300 ± 0.020 (7.62 ± 0.5) | 0.350 ± 0.020 (8.9 ± 0.5) | | | | | | | | | | | | | | |
| | Leads per side | - | - | 2 | 2 | 2 | 2 | 3 | | | | | | | | | | | | | | |
| | T max.* | 0.154 (3.9) | 0.138 (3.5) | 0.138 (3.5) | 0.2kV up to 3kV: 0.119 [3] 4kV-5kV: 0.150 [3.8] | 0.2kV up to 3kV: 0.158 [4] 4kV-5kV: 0.197 [5] | 0.2kV up to 3kV: 0.158 [4] 4kV: 0.197 [5] 5kV: 0.237 [6] | 0.2kV up to 3kV: 0.158 [4] 4kV: 0.197 [5] 5kV: 0.237 [6] | | | | | | | | | | | | | | |
| Dielectric | NPO | X7R | NPO | C4xx | X7R | NPO | C4xx | X7R | NPO | C4xx | X7R | NPO | C4xx | X7R | NPO | C4xx | X7R | NPO | C4xx | X7R | | |
| Exxelia ceramic code | 1 | 2 | 1 | 4 | 2 | 1 | 4 | 2 | 1 | 4 | 2 | 1 | 4 | 2 | 1 | 4 | 2 | 1 | 4 | 2 | | |
| Min. Capacitance value | 12pF | 120pF | 10pF | 27pF | 100pF | 10pF | 33pF | 150pF | 10pF | 33pF | 150pF | 15pF | 47pF | 150pF | 18pF | 56pF | 150pF | 33pF | 82pF | 330pF | | |
| Rated voltage (U _{RC}) | 0.2kV | Standard | - | - | 5.6nF | 120nF | 220nF | 12nF | 220nF | 470nF | 12nF | 220nF | 390nF | 15nF | 330nF | 560nF | 18nF | 390nF | 820nF | 33nF | 680nF | 1.5µF |
| | | Extended | - | - | 18nF | - | 470nF | 27nF | - | - | 22nF | - | 1µF | 39nF | - | - | 56nF | - | 1.8µF | 100nF | - | 2.7µF |
| | 0.5kV | Standard | - | - | 3.3nF | 22nF | 47nF | 6.8nF | 47nF | 100nF | 5.6nF | 47nF | 100nF | 6.8nF | 68nF | 150nF | 8.2nF | 82nF | 220nF | 22nF | 120nF | 390nF |
| | | Extended | - | - | 10nF | 39nF | 150nF | 18nF | 68nF | - | 18nF | 68nF | 270nF | 22nF | 100nF | - | 27nF | 120nF | 560nF | 68nF | 220nF | 1µF |
| | 1kV | Standard | - | - | 1.8nF | 6.8nF | 15nF | 2.7nF | 12nF | 22nF | 2.2nF | 12nF | 22nF | 3.3nF | 18nF | 33nF | 3.9nF | 22nF | 47nF | 10nF | 39nF | 68nF |
| | | Extended | 820pF | 12nF | 5.6nF | 10nF | 27nF | 8.2nF | 15nF | - | 6.8nF | 15nF | 56nF | 10nF | 22nF | - | 12nF | 27nF | 120nF | 33nF | 56nF | 220nF |
| | 1.5kV | Standard | - | - | 820pF | 2.7nF | 5.6nF | 1.2nF | 5.6nF | 10nF | 1.5nF | 5.6nF | 10nF | 2.2nF | 8.2nF | 15nF | 2.7nF | 10nF | 18nF | 4.7nF | 18nF | 33nF |
| | | Extended | - | - | 1.5nF | 3.9nF | 12nF | 2.2nF | 8.2nF | - | 2.2nF | 6.8nF | 22nF | 3.3nF | 12nF | - | 4.7nF | 15nF | 47nF | 8.2nF | 27nF | 82nF |
| | 2kV | Standard | - | - | 390pF | 1.5nF | 3.3nF | 680pF | 2.7nF | 5.6nF | 470pF | 2.7nF | 5.6nF | 820pF | 4.7nF | 6.8nF | 1.2nF | 5.6nF | 10nF | 3.3nF | 10nF | 18nF |
| | | Extended | 470pF | 2.7nF | 820pF | 2.2nF | 5.6nF | 1.2nF | 3.9nF | - | 1nF | 3.9nF | 12nF | 1.8nF | 6.8nF | - | 2.7nF | 8.2nF | 27nF | 6.8nF | 15nF | 47nF |
| | 3kV | Standard | - | - | 180pF | 680pF | 1.2nF | 180pF | 1.2nF | 2.2nF | 220pF | 1.2nF | 2.2nF | 330pF | 1.8nF | 3.3nF | 470pF | 2.2nF | 3.9nF | 820pF | 3.9nF | 6.8nF |
| | | Extended | 220pF | 1nF | 390pF | 1nF | 2.7nF | 680pF | 1.8nF | - | 470pF | 1.8nF | 4.7nF | 820pF | 2.7nF | - | 1nF | 3.3nF | 12nF | 1.8nF | 5.6nF | 22nF |
| 4kV | Standard | - | - | 100pF | 330pF | 680pF | 120pF | 680pF | 1nF | 150pF | 820pF | 1.2nF | 220pF | 1.2nF | 1.8nF | 390pF | 1.5nF | 2.7nF | 680pF | 3.3nF | 4.7nF | |
| | Extended | 150pF | 470pF | 220pF | 560pF | - | 330pF | 1nF | - | 330pF | 1.2nF | 2.2nF | 680pF | 1.8nF | - | 820pF | 2.2nF | 4.7nF | 1.5nF | 4.7nF | 10nF | |
| 5kV | Standard | - | - | - | - | - | - | - | - | 100pF | 560pF | 820pF | 150pF | 820pF | 1nF | 270pF | 1nF | 1.8nF | 470pF | 2.2nF | 3.3nF | |
| | Extended | - | - | - | - | - | - | - | - | 220pF | 820pF | 1.5nF | 320pF | 1.2nF | - | 560pF | 1.5nF | 3.3nF | 1nF | 2.7nF | 6.8nF | |

High Voltage Chips Capacitors

C Series

STANDARD RATINGS

| Size | 4040 | | | 5440 | | | 5550 | | | 6560 | | | 11283 | | | 16080 | | | | |
|----------------------------------|----------------|---|-------|-------|---|-------|-------|---|-------|-------|---|-------|-------|---|-------|-------|---|-------|-------|-------|
| Exxelia size code | 83 | | | 84 | | | 89 | | | 85 | | | 87 | | | 88 | | | | |
| Dimensions inches (mm) | L* | 0.400 ± 0.039 (10.16 ± 1) | | | 0.539 ± 0.039 (13.7 ± 1) | | | 0.551 ± 0.039 (14 ± 1) | | | 0.650 ± 0.039 (16.5 ± 1) | | | 1.122 ± 0.039 (28.5 ± 1) | | | 1.555 ± 0.039 (39.5 ± 1) | | | |
| | W* | 0.400 ± 0.039 (10.16 ± 1) | | | 0.400 ± 0.039 (10.16 ± 1) | | | 0.500 ± 0.039 (12.7 ± 1) | | | 0.598 ± 0.039 (15.2 ± 1) | | | 0.827 ± 0.039 (21 ± 1) | | | 0.756 ± 0.039 (19.2 ± 1) | | | |
| | a | 0.059 ± 0.020 (1.5 ± 0.5) | | | 0.059 ± 0.020 (1.5 ± 0.5) | | | 0.059 ± 0.020 (1.5 ± 0.5) | | | 0.059 ± 0.020 (1.5 ± 0.5) | | | 0.059 ± 0.020 (1.5 ± 0.5) | | | 0.059 ± 0.020 (1.5 ± 0.5) | | | |
| | d | 0.138 ± 0.008 (3.5 ± 0.2) | | | 0.138 ± 0.008 (3.5 ± 0.2) | | | 0.138 ± 0.008 (3.5 ± 0.2) | | | 0.138 ± 0.008 (3.5 ± 0.2) | | | 0.138 ± 0.008 (3.5 ± 0.2) | | | 0.138 ± 0.008 (3.5 ± 0.2) | | | |
| | b | 0.315 ± 0.020 (8 ± 0.5) | | | 0.315 ± 0.020 (8 ± 0.5) | | | 0.315 ± 0.020 (8 ± 0.5) | | | 0.591 ± 0.020 (15 ± 0.5) | | | 0.591 ± 0.020 (15 ± 0.5) | | | 0.591 ± 0.020 (15 ± 0.5) | | | |
| | R min. | 0.275 (7) | | | 0.393 (10) | | | 0.393 (10) | | | 0.511 (13) | | | 0.984 (25) | | | 1.377 (35) | | | |
| | C max. | 0.473 (12) | | | 0.611 (15.5) | | | 0.63 (16) | | | 0.729 (18.5) | | | 1.26 (32) | | | 1.654 (42) | | | |
| | X | 0.45 ± 0.020 (11.43 ± 0.5) | | | 0.551 ± 0.020 (14 ± 0.5) | | | 0.563 ± 0.020 (14.3 ± 0.5) | | | 0.7 ± 0.020 (17.78 ± 0.5) | | | 1.15 ± 0.020 (29.21 ± 0.5) | | | 1.6 ± 0.020 (40.64 ± 0.5) | | | |
| | Leads per side | 4 | | | 4 | | | 5 | | | 6 | | | 6 | | | 6 | | | |
| | T max.* | 0.2kV up to 3kV: 0.158 (4) 4kV: 0.197 (5) 5kV up to 10kV: 0.237 (6) | | | 0.2kV up to 3kV: 0.158 (4) 4kV: 0.197 (5) 5kV up to 10kV: 0.237 (6) | | | 0.2kV up to 3kV: 0.158 (4) 4kV: 0.197 (5) 5kV up to 10kV: 0.237 (6) | | | 0.2kV up to 3kV: 0.158 (4) 4kV: 0.197 (5) 5kV up to 10kV: 0.237 (6) | | | 0.2kV up to 3kV: 0.158 (4) 4kV: 0.197 (5) 5kV: 0.237 (6) 7.5kV up to 10kV: 0.256 (6.5) | | | 0.2kV up to 3kV: 0.158 (4) 4kV: 0.197 (5) 5kV: 0.236 (6) 7.5kV up to 10kV: 0.256 (6.5) | | | |
| Dielectric | | | | | | | | | | | | | | | | | | | | |
| Exxelia ceramic code | | | | | | | | | | | | | | | | | | | | |
| Min. Capacitance value | | | | | | | | | | | | | | | | | | | | |
| Rated voltage (U _{RC}) | | | | | | | | | | | | | | | | | | | | |
| | | | | | | | | | | | | | | | | | | | | |
| | 0.2kV | Standard | 56nF | 1.2µF | 2.7µF | 82nF | 1.5µF | 3.9µF | 100nF | 1.8µF | 4.7µF | 180nF | 2.7µF | 6.8µF | 330nF | 6.8µF | 12µF | 390nF | 8.2µF | 15µF |
| | | Extended | 180nF | - | 5.6µF | 270nF | - | 6.8µF | 220nF | - | 8.2µF | 560nF | - | 12µF | 1µF | - | 33µF | 1.2µF | - | 39µF |
| | 0.5kV | Standard | 33nF | 270nF | 680nF | 47nF | 330nF | 1µF | 56nF | 390nF | 1.2µF | 82nF | 680nF | 1.8µF | 150nF | 1.5µF | 3.9µF | 270nF | 1.8µF | 4.7µF |
| | | Extended | 100nF | 390nF | 1.5µF | 150nF | 560nF | 2.2µF | 150nF | 680nF | 2.7µF | 270nF | 1µF | 3.9µF | 470nF | 2.2µF | 10µF | 820nF | 2.7µF | 12µF |
| | 1kV | Standard | 15nF | 82nF | 150nF | 22nF | 82nF | 220nF | 33nF | 120nF | 270nF | 39nF | 220nF | 390nF | 82nF | 560nF | 1µF | 150nF | 680nF | 1.2µF |
| | | Extended | 47nF | 120nF | 390nF | 68nF | 120nF | 560nF | 82nF | 220nF | 560nF | 120nF | 330nF | 1µF | 270nF | 680nF | 2.7µF | 470nF | 1µF | 3.3µF |
| | 1.5kV | Standard | 8.2nF | 39nF | 82nF | 12nF | 39nF | 100nF | 15nF | 68nF | 150nF | 22nF | 100nF | 180nF | 47nF | 220nF | 470nF | 68nF | 330nF | 560nF |
| | | Extended | 18nF | 56nF | 180nF | 22nF | 56nF | 220nF | 33nF | 100nF | 330nF | 47nF | 150nF | 470nF | 100nF | 330nF | 1.2µF | 150nF | 470nF | 1.5µF |
| | 2kV | Standard | 4.7nF | 18nF | 33nF | 6.8nF | 22nF | 68nF | 8.2nF | 39nF | 68nF | 12nF | 56nF | 100nF | 27nF | 120nF | 220nF | 39nF | 180nF | 330nF |
| | | Extended | 10nF | 27nF | 100nF | 15nF | 33nF | 150nF | 18nF | 56nF | 150nF | 27nF | 82nF | 220nF | 56nF | 180nF | 560nF | 82nF | 270nF | 820nF |
| | 3kV | Standard | 1.5nF | 8.2nF | 15nF | 2.7nF | 10nF | 27nF | 3.3nF | 18nF | 27nF | 4.7nF | 27nF | 39nF | 12nF | 56nF | 100nF | 15nF | 68nF | 120nF |
| | | Extended | 3.3nF | 12nF | 39nF | 5.6nF | 15nF | 56nF | 10nF | 22nF | 68nF | 10nF | 39nF | 100nF | 27nF | 82nF | 270nF | 33nF | 100nF | 330nF |
| | 4kV | Standard | 1.2nF | 6.8nF | 10nF | 2.2nF | 6.8nF | 15nF | 2.7nF | 12nF | 18nF | 3.9nF | 18nF | 27nF | 10nF | 39nF | 68nF | 12nF | 47nF | 100nF |
| | | Extended | 2.7nF | 10nF | 18nF | 4.7nF | 10nF | 27nF | 6.8nF | 18nF | 39nF | 8.2nF | 27nF | 47nF | 22nF | 56nF | 120nF | 27nF | 82nF | 150nF |
| | 5kV | Standard | 1nF | 4.7nF | 5.6nF | 1.8nF | 4.7nF | 10nF | 1.8nF | 8.2nF | 12nF | 3.3nF | 12nF | 18nF | 8.2nF | 27nF | 56nF | 10nF | 33nF | 68nF |
| | | Extended | 2.2nF | 6.8nF | 15nF | 3.9nF | 6.8nF | 22nF | 4.7nF | 12nF | 27nF | 6.8nF | 18nF | 39nF | 15nF | 39nF | 82nF | 18nF | 47nF | 100nF |
| | 7.5kV | Standard | 150pF | - | 1.5nF | 270pF | - | 2.7nF | 470pF | - | 3.3nF | 560pF | - | 6.8nF | 1.5nF | - | 18nF | 2.2nF | - | 27nF |
| | | Extended | 330pF | - | 3.3nF | 560pF | - | 5.6nF | 1.2nF | - | 6.8nF | 1.2nF | - | 12nF | 3.3nF | - | 33nF | 4.7nF | - | 47nF |
| 10kV | Standard | 100pF | - | 680pF | 180pF | - | 1.2nF | 270pF | - | 1.5nF | 390pF | - | 3.3nF | 1nF | - | 8.2nF | 1.5nF | - | 12nF | |
| | Extended | 220pF | - | 1.8nF | 390pF | - | 3.3nF | 680pF | - | 3.9nF | 820pF | - | 6.8nF | 2.2nF | - | 15nF | 3.3nF | - | 27nF | |

* For E, H and HW: add +0.020 inch (+0.5 mm) to L, W and T dimensions.
 The high voltage parts may require varnish or encapsulation to prevent surface arcing.
 Available capacitance values:
 NPO, C4xx dielectrics: E6, E12, E24 (see page 14). Specific values upon request.
 X7R dielectric: E6, E12 in standard (see page 14). Specific values upon request.
 The above table defines the standard products, other components may be built upon request.

HIGH VOLTAGE


General Information

High voltage multilayer ceramic capacitors designed by EXXELIA are adapted to applications in electronics such as high voltage power supplies and high circuits. Their multilayer construction offers significant size and space saving advantages. They are available in class 1 (NPO), class 2 (X7R) and C4xx (-2,200 ppm/°C) dielectrics versions complying with the main requirements of applicable standards. They are suited for use in commercial, industrial and High-Rel military and space circuits.

As standard products can't meet all the specificities of all applications, special applications may require specific features (higher voltage, burn-in, dimensions, coating, leading, marking...) not described in this catalogue. Based on our state-of-the-art technologies and our expertise, our Engineers may study at your request all special components to meet your application.

Please, consult us for more information.


NPO, X7R, C4xx: SELF-RESONANCE FREQUENCY VS CAPACITANCE




NPO/COG DIELECTRICS (CLASS 1)

Made of titanium oxide and other various selected oxides, they feature unique stability of all parameters under such constraints as operating time, temperature, voltage applied. For example, the quality factor remains very high over an extremely wide frequency range. As example, loss angle tangent value at 1MHz is typically in the order of $3 \cdot 10^{-4}$. These characteristics make them compatible with steep-edge impulse mode without noticeable temperature rise. The different parameters and related variations are illustrated in figures below:


NPO: RELATIVE CAPACITANCE CHANGE VS TEMPERATURE




NPO: IMPEDANCE VS FREQUENCY



NPO: LOSS TANGENT VS TEMPERATURE



NPO: INSULATION RESISTANCE VS TEMPERATURE



General Information


X7R DIELECTRICS (CLASS 2)

They are mainly made of barium titanate modified by various oxides to achieve the electrical properties required. A specific ceramic dielectric is used to achieve an excellent dielectric strength. High dielectric constant enables to achieve high capacitance values.


For optimum use, the specific properties of barium titanate in function of the different parameters must be taken into account.

See the variations illustrated in figures below:


CHANGE VS PERCENTAGE OF RATED VOLTAGE APPLIED




X7R: CAPACITANCE CHANGE VS TEMPERATURE



X7R: CAPACITANCE CHANGE VS FREQUENCY




X7R: INSULATION RESISTANCE VS TEMPERATURE




HIGH VOLTAGE

General Information

X7R: LOSS TANGENT CHANGE VS TEMPERATURE




X7R: MAXIMUM ADMISSIBLE CURRENT VS FREQUENCY




These typical curves are examples of admissible currents for one family of chip capacitors (size 3333). For other curves and products or for further information, please contact us.

Note: for the calculations, we have considered that the terminations are directly connected to an infinite heat sink. In other words, the thermal resistance of the circuit itself which depends on its type and design has not been taken into account. Moreover, the ambient temperature taken is 25°C.

X7R: LOSS TANGENT CHANGE VS FREQUENCY



X7R: ESR VS FREQUENCY




The ESR (Equivalent Serial Resistance) typical curves are given, here for SMD (chip) capacitors. Regarding the curves for the leaded capacitors, they are rather the same. Indeed, due to the resistivity of the raw material used and the wire diameters, the resistance of the wires is much lower than the ESR of the chips. So, in a first approach, their influence can be considered as negligible.

General Information


C4xx DIELECTRIC

This ceramic is a negative temperature coefficient dielectric [-2,200 ppm/°C]. Its advantage is that it combines the high dielectric constant of an X7R dielectric with the stability of an NPO dielectric. As the C4xx ceramic features low dissipation factor it is recommended for AC line filtering from 110 Vrms to 230 Vrms, 20 to 400 Hz, for high power RF at high voltage up to 5,000 V and for pulse applications.


C4xx: TEMPERATURE COEFFICIENT



C4xx: VOLTAGE COEFFICIENT




COMPARISON OF CAPACITANCE VALUE UNDER RATED VOLTAGE AT 125°C




HIGH VOLTAGE

COMPARISON OF SELF-HEATING AT 400 Hz BETWEEN C4xx AND X7R DIELECTRICS



General Information

RECOMMENDED FOOTPRINTS




DIMENSIONS in inches (mm)

| Exxelia size code | Lead shape | C max inches (mm) | Leads per side | d inches (mm) | b inches (mm) | C ₁ inches (mm) | W ₁ inches (mm) | I ₁ inches (mm) | I ₂ inches (mm) | I ₃ inches (mm) |
|-------------------|------------|-------------------|----------------|---------------------------|-------------------------|----------------------------|----------------------------|----------------------------|----------------------------|----------------------------|
| 90 | P* | 0.228 (5.8) | 2 | 0.06 ± 0.012 (1.5 ± 0.3) | - | 0.268 (6.8) | 0.147 (3.74) | 0.047 (1.2) | 0.108 (2.75) | 0.098 (2.5) |
| | L | 0.394 (10) | 2 | 0.098 ± 0.02 (2.5 ± 0.5) | - | 0.433 (11) | 0.147 (3.74) | 0.047 (1.2) | 0.152 (3.85) | 0.130 (3.3) |
| | R | 0.386 (9.8) | 1 | 0.087 ± 0.008 (2.2 ± 0.2) | 0.197 ± 0.02 (5 ± 0.5) | 0.425 (10.8) | 0.244 (6.2) | - | 0.148 (3.75) | 0.130 (3.3) |
| 80 | P* | 0.276 (7) | 2 | 0.06 ± 0.012 (1.5 ± 0.3) | - | 0.315 (8) | 0.147 (3.74) | 0.047 (1.2) | 0.108 (2.75) | 0.098 (2.5) |
| | L | 0.480 (12.2) | 2 | 0.098 ± 0.02 (2.5 ± 0.5) | - | 0.520 (13.2) | 0.147 (3.74) | 0.047 (1.2) | 0.171 (4.35) | 0.177 (4.5) |
| | R | 0.433 (11) | 1 | 0.087 ± 0.008 (2.2 ± 0.2) | 0.197 ± 0.02 (5 ± 0.5) | 0.472 (12) | 0.244 (6.2) | - | 0.148 (3.75) | 0.177 (4.5) |
| 91 | P* | 0.276 (7) | 2 | 0.06 ± 0.012 (1.5 ± 0.3) | - | 0.315 (8) | 0.147 (3.74) | 0.047 (1.2) | 0.108 (2.75) | 0.098 (2.5) |
| | L | 0.480 (12.2) | 2 | 0.098 ± 0.02 (2.5 ± 0.5) | - | 0.520 (13.2) | 0.147 (3.74) | 0.047 (1.2) | 0.171 (4.35) | 0.177 (4.5) |
| | R | 0.433 (11) | 1 | 0.087 ± 0.008 (2.2 ± 0.2) | 0.197 ± 0.02 (5 ± 0.5) | 0.472 (12) | 0.244 (6.2) | - | 0.148 (3.75) | 0.177 (4.5) |
| 81 | P* | 0.315 (8) | 2 | 0.087 ± 0.012 (2.2 ± 0.3) | - | 0.354 (9) | 0.147 (3.74) | 0.047 (1.2) | 0.108 (2.75) | 0.138 (3.5) |
| | L | 0.531 (13.5) | 2 | 0.098 ± 0.02 (2.5 ± 0.5) | - | 0.571 (14.5) | 0.147 (3.74) | 0.047 (1.2) | 0.171 (4.35) | 0.228 (5.8) |
| | R | 0.484 (12.3) | 1 | 0.087 ± 0.008 (2.2 ± 0.2) | 0.197 ± 0.02 (5 ± 0.5) | 0.524 (13.3) | 0.244 (6.2) | - | 0.148 (3.75) | 0.228 (5.8) |
| 82 | P* | 0.354 (9) | 3 | 0.087 ± 0.012 (2.2 ± 0.3) | - | 0.394 (10) | 0.247 (6.28) | 0.047 (1.2) | 0.108 (2.75) | 0.177 (4.5) |
| | L | 0.587 (14.9) | 3 | 0.098 ± 0.02 (2.5 ± 0.5) | - | 0.626 (15.9) | 0.247 (6.28) | 0.047 (1.2) | 0.171 (4.35) | 0.283 (7.2) |
| | R | 0.642 (16.3) | 1 | 0.138 ± 0.008 (3.5 ± 0.2) | 0.315 ± 0.02 (8 ± 0.5) | 0.681 (17.3) | 0.362 (9.2) | - | 0.199 (5.05) | 0.283 (7.2) |
| 83 | P* | 0.472 (12) | 4 | 0.087 ± 0.012 (2.2 ± 0.3) | - | 0.512 (13) | 0.347 (8.82) | 0.047 (1.2) | 0.118 (3) | 0.276 (7) |
| | L | 0.676 (17.16) | 4 | 0.098 ± 0.02 (2.5 ± 0.5) | - | 0.715 (18.16) | 0.347 (8.82) | 0.047 (1.2) | 0.191 (4.85) | 0.333 (8.46) |
| | R | 0.731 (18.56) | 1 | 0.138 ± 0.008 (3.5 ± 0.2) | 0.315 ± 0.02 (8 ± 0.5) | 0.770 (19.56) | 0.362 (9.2) | - | 0.219 (5.55) | 0.333 (8.46) |
| 84 | P* | 0.610 (15.5) | 4 | 0.087 ± 0.012 (2.2 ± 0.3) | - | 0.650 (16.5) | 0.347 (8.82) | 0.047 (1.2) | 0.128 (3.25) | 0.394 (10) |
| | L | 0.815 (20.7) | 4 | 0.098 ± 0.02 (2.5 ± 0.5) | - | 0.854 (21.7) | 0.347 (8.82) | 0.047 (1.2) | 0.191 (4.85) | 0.472 (12) |
| | R | 0.870 (22.1) | 1 | 0.138 ± 0.008 (3.5 ± 0.2) | 0.315 ± 0.02 (8 ± 0.5) | 0.909 (23.1) | 0.362 (9.2) | - | 0.219 (5.55) | 0.472 (12) |
| 89 | P* | 0.630 (16) | 5 | 0.087 ± 0.012 (2.2 ± 0.3) | - | 0.669 (17) | 0.347 (8.82) | 0.047 (1.2) | 0.128 (3.25) | 0.413 (10.5) |
| | L | 0.827 (21) | 5 | 0.098 ± 0.02 (2.5 ± 0.5) | - | 0.866 (22) | 0.347 (8.82) | 0.047 (1.2) | 0.191 (4.85) | 0.484 (12.3) |
| | R | 0.882 (22.4) | 1 | 0.138 ± 0.008 (3.5 ± 0.2) | 0.315 ± 0.02 (8 ± 0.5) | 0.921 (23.4) | 0.362 (9.2) | - | 0.219 (5.55) | 0.484 (12.3) |
| 85 | P* | 0.728 (18.5) | 6 | 0.087 ± 0.012 (2.2 ± 0.3) | - | 0.768 (19.5) | 0.547 (13.9) | 0.047 (1.2) | 0.128 (3.25) | 0.512 (13) |
| | L | 0.925 (23.5) | 6 | 0.098 ± 0.02 (2.5 ± 0.5) | - | 0.965 (24.5) | 0.547 (13.9) | 0.047 (1.2) | 0.191 (4.85) | 0.583 (14.8) |
| | R | 0.980 (24.9) | 1 | 0.138 ± 0.008 (3.5 ± 0.2) | 0.591 ± 0.02 (15 ± 0.5) | 1.020 (25.9) | 0.638 (16.2) | - | 0.219 (5.55) | 0.583 (14.8) |
| 87 | P* | 1.260 (32) | 6 | 0.087 ± 0.012 (2.2 ± 0.3) | - | 1.299 (33) | 0.547 (13.9) | 0.047 (1.2) | 0.128 (3.25) | 0.945 (24) |
| | L | 1.398 (35.5) | 6 | 0.098 ± 0.02 (2.5 ± 0.5) | - | 1.437 (36.5) | 0.547 (13.9) | 0.047 (1.2) | 0.191 (4.85) | 1.055 (26.8) |
| | R | 1.453 (36.9) | 1 | 0.138 ± 0.008 (3.5 ± 0.2) | 0.591 ± 0.02 (15 ± 0.5) | 1.492 (37.9) | 0.638 (16.2) | - | 0.219 (5.55) | 1.055 (26.8) |
| 88 | P* | 1.654 (42) | 6 | 0.087 ± 0.012 (2.2 ± 0.3) | - | 1.693 (43) | 0.547 (13.9) | 0.047 (1.2) | 0.128 (3.25) | 1.378 (35) |
| | L | 1.831 (46.5) | 6 | 0.098 ± 0.02 (2.5 ± 0.5) | - | 1.870 (47.5) | 0.547 (13.9) | 0.047 (1.2) | 0.191 (4.85) | 1.488 (37.8) |
| | R | 1.886 (47.9) | 1 | 0.138 ± 0.008 (3.5 ± 0.2) | 0.591 ± 0.02 (15 ± 0.5) | 1.925 (48.9) | 0.638 (16.2) | - | 0.219 (5.55) | 1.488 (37.8) |

* For PL and PLS, add 0.098 in (2.5 mm) to d and I₂ and 0.197 in (5 mm) to C₁.


Ceramic Capacitors Technology

MLCC STRUCTURE



EQUIVALENT CIRCUIT

Capacitor is a complex component combining resistive, inductive and capacitive phenomena. A simplified schematic for the equivalent circuit is:



DIELECTRIC CHARACTERISTICS

Insulation Resistance (IR) is the resistance measured under DC voltage across the terminals of the capacitor and consists principally of the parallel resistance shown in the equivalent circuit. As capacitance values and hence the area of dielectric increases, the IR decreases and hence the product $[C \times IR]$ is often specified in $\Omega \cdot F$ or $M\Omega \cdot \mu F$.

The Equivalent Series Resistance (ESR) is the sum of the resistive terms which generate heating when capacitor is used under AC voltage at a given frequency (f) .

Dissipation factor (DF) is the ration of the apparent power input will turn to heat in the capacitor:

$$DF = 2\pi f C ESR$$

When a capacitor works under AC voltage, **heat power loss (P)**, expressed in Watt, is equal to:

$$P = 2\pi f C V_{rms}^2 DF$$

The series inductance (Ls) is due to the currents running through the electrodes. It can distort the operation of the capacitor at high frequency where the **impedance (Z)** is given as:

$$Z = R_s + j [L_s \cdot \omega - 1/(C \cdot \omega)] \text{ with } \omega = 2\pi f$$

When frequency rises, the capacitive component of capacitors is gradually canceled up to the resonance frequency, where :

$$Z = R_s \text{ and } L_s C \cdot \omega^2 = 1$$

Above this frequency the capacitor behaves like an inductor.

| | P100 | NPO | N2200 (C4xx) | BX | 2C1 | X7R |
|--|--|---|---------------------------|---------------------------------------|---------|----------------|
| Dielectric material | Porcelain | Magnesium titanate or Neodymium baryum titanate | Barium zirconate titanate | Baryum titanate (BaTiO ₃) | | |
| Dielectric constant | 15 – 18 | 20 – 85 | 450 | 2,000 – 5,000 | | |
| Electrode technology | PME (Precious Metal Electrodes): Ag/Pd | | | | | |
| Capacitance variation between –55°C and +125°C without DC voltage | [100±30]ppm/°C | [0±30]ppm/°C | [–2,200±500] ppm/°C | ±15% | ±20% | ±15% |
| Capacitance variation between –55°C and +125°C with DC rated voltage | | | 0-15% | 15%–25% | 20%–30% | Not applicable |
| Piezo-electric effect | None | | None | Yes | | |
| Dielectric absorption | None | | Few % | Few % | | |
| Thermal shock sensitive | + | | + | ++ | | |

Ceramic Capacitors Technology


MANUFACTURING STEPS

SLIP CASTING




A slurry, a mix of ceramic powder, binder and solvents, is poured onto conveyor belt inside a drying oven, resulting in a dry ceramic sheet.

ELECTRODE SCREEN PRINTING




The electrode ink, made from a metal powder mixed with solvents, is printed onto the ceramic sheets using a screen printing process.

STACKING




The sheets with electrode printed are stacked to create a multilayer structure.

TERMINATIONS




Each terminal of the capacitor is dipped in the termination ink, mix of metal powder, solvents and glass frit and the parts are fired in an oven.

SINTERING




The parts are sintered in an oven with a precise temperature profile which is very important to the characteristics of the capacitors.

PRESSING




Pressure is applied to the stack to fuse all the separate layers, this created a monolithic structure.

TERMINATIONS PLATING



Stacking + leads soldering + encapsulation
[see pages 10-11]

FINAL TESTING



PACKAGING



User Guide

SMD TERMINATIONS

| NON RoHS COMPLIANT | Code | RoHS COMPLIANT | Code | Recommended mounting process | | | | | | | Storage (months)* |
|------------------------------------|------|---------------------------|--------|------------------------------|---------------|----------------|----------------|-----------------------|--------------------|--------------|-------------------|
| | | | | Magnetic | Epoxy bonding | Iron soldering | Wave soldering | Vapor phase soldering | Infrared soldering | Wire bonding | |
| Ag | Q | Ag | QW / P | No | • | • | • | • | | | 18 |
| Ag/Pd/Pt | - | Ag/Pd/Pt | W / A | No | • | • | • | | | | 24 |
| Ag/Pd/Pt + dipped Sn/Pb 60/40 | H | Ag/Pd/Pt + dipped Sn | HW | No | | • | | | | | 24 |
| Ag + Ni + electrolytic Sn/Pb 95/5 | C | Ag + Ni + electrolytic Sn | CW / S | Yes | | • | • | • | • | | 18 |
| Ag + Ni + electrolytic Sn/Pb 60/40 | D | - | - | Yes | | • | • | • | • | | 18 |
| - | - | Ag + Cu + electrolytic Sn | C** | No | | • | • | • | • | | 18 |
| Ag + Ni + dipped Sn/Pb 60/40 | E | - | - | Yes | | • | • | | | | 24 |
| Ag + Ni + Au | G | Ag + Ni + Au | GW | Yes | • | • | • | • | • | • | 36 |
| Ag + Polymer + Ni + Sn/Pb 95/5 | YC | Ag + Polymer + Ni + Sn | YCW | Yes | | • | • | • | • | | 18 |
| Ag + Polymer + Ni + Sn/Pb 60/40 | YD | - | - | Yes | | • | • | • | • | | 18 |
| Ag + Polymer + Ni + Au | YG | Ag + Polymer + Ni + Au | YGW | Yes | • | • | • | • | • | • | 36 |

Nickel (Ni) or Copper (Cu) barriers amplify thermal shock and are not recommended for chip sizes larger than 3030.

* Storage must be in a dry environment at a temperature of 20°C with a relative humidity below 50%, or preferably in a package enclosing a desiccant.

** Non magnetic chips series only.

SMD ENVIRONMENTAL TESTS

Ceramic chip capacitors for SMD are designed to meet test requirements of **CECC 32100** and **NF C 93133** standards as specified below in compliance with **NF C 20700** and **IEC 68** standards:

- Solderability: **NF C 20758**, 260°C, bath 62/36/2.
- Adherence: 5N force.
- Vibration fatigue test: **NF C 20706**, 20 g, 10 Hz to 2,000 Hz, 12 cycles of 20 minutes each.
- Rapid temperature change: **NF C 20714**, -55°C to + 125°C, 5 cycles.
- Combined climatic test: **IEC 68-2-38**.
- Damp heat: **NF C 20703**, 93 %, H.R., 40°C.
- Endurance test: 1,000 hours, 1.5 U_{RC}, 125°C.

STORAGE OF CHIP CAPACITORS

TINNED OR NON TINNED CHIP CAPACITORS

Storage must be in a dry environment at a temperature of 20°C with a relative humidity below 50 %, or preferably in a packaging enclosing a desiccant.

STORAGE IN INDUSTRIAL ENVIRONMENT:

- 2 years for tin dipped chip capacitors,
- 18 months for tin electroplated chip capacitors,
- 2 years for non tinned chip capacitors,
- 3 years for gold plated chip capacitors.

STORAGE IN CONTROLLED NEUTRAL NITROGEN ENVIRONMENT:

- 4 years for tin dipped or electroplated chip capacitors,
- 4 years for non tinned chip capacitors,
- 5 years for gold plated chip capacitors.

Storage duration should be considered from delivery date and not from batch manufacture date. The tests carried out at final acceptance stage [solderability, susceptibility to solder heat] enable to assess the compatibility to surface mounting of the chips.

User Guide

LEAD STYLES


SURFACE MOUNTING

DIL LEADS

P style



PL style



L style



J style




RIBBON LEADS

Micro-strip (type 1)
Short Micro-strip (type 1S)



Axial (Type 2)



Radial (Type 3)



R style



RX style



RJ style



Please contact Exxelia sales for any lead configuration not shown.

TROUGH-HOLE MOUNTING

AXIAL AND RADIAL

Radial leads (Type 6)



Radial leads (4 leads)



Axial leads (Type 7)



DIL leads: N style



ENCAPSULATION STYLES

Ceramic encapsulation
(selfprotected)



Varnish



Conformal coating




Molding



User Guide

SOLDERING ADVICES FOR REFLOW SOLDERING



| Dimensions in inches (in mm) | Reflow soldering | | | | | | Wave soldering | | | | | |
|------------------------------|------------------|--------|----------------|--------|----------------|-------|----------------|--------|----------------|--------|----------------|-------|
| | l ₁ | | l ₂ | | l ₃ | | l ₁ | | l ₂ | | l ₃ | |
| 0402 | 0.043 | (1.1) | 0.035 | (0.9) | 0.012 | (0.3) | 0.043 | (1.1) | 0.047 | (1.2) | 0.012 | (0.3) |
| 0403 | 0.055 | (1.4) | 0.035 | (0.9) | 0.012 | (0.3) | 0.055 | (1.4) | 0.047 | (1.2) | 0.012 | (0.3) |
| 0504 | 0.063 | (1.6) | 0.051 | (1.3) | 0.016 | (0.4) | 0.063 | (1.6) | 0.063 | (1.6) | 0.016 | (0.4) |
| 0603 | 0.055 | (1.4) | 0.059 | (1.5) | 0.02 | (0.5) | 0.055 | (1.4) | 0.071 | (1.8) | 0.02 | (0.5) |
| 0805 | 0.073 | (1.85) | 0.065 | (1.65) | 0.024 | (0.6) | 0.073 | (1.85) | 0.077 | (1.95) | 0.024 | (0.6) |
| 0907 | 0.094 | (2.4) | 0.065 | (1.65) | 0.035 | (0.9) | 0.094 | (2.4) | 0.077 | (1.95) | 0.035 | (0.9) |
| 1005 | 0.073 | (1.85) | 0.067 | (1.7) | 0.039 | (1) | 0.073 | (1.85) | 0.079 | (2) | 0.039 | (1) |
| 1206 | 0.083 | (2.1) | 0.067 | (1.7) | 0.059 | (1.5) | 0.083 | (2.1) | 0.079 | (2) | 0.059 | (1.5) |
| 1210 | 0.118 | (3) | 0.069 | (1.75) | 0.059 | (1.5) | 0.118 | (3) | 0.081 | (2.05) | 0.059 | (1.5) |
| 1605 | 0.073 | (1.85) | 0.071 | (1.8) | 0.087 | (2.2) | 0.073 | (1.85) | 0.083 | (2.1) | 0.087 | (2.2) |
| 1806 | 0.087 | (2.2) | 0.073 | (1.85) | 0.102 | (2.6) | 0.087 | (2.2) | 0.085 | (2.15) | 0.102 | (2.6) |
| 1812 | 0.152 | (3.85) | 0.073 | (1.85) | 0.102 | (2.6) | 0.152 | (3.85) | 0.085 | (2.15) | 0.102 | (2.6) |
| 1825 | 0.281 | (7.15) | 0.073 | (1.85) | 0.102 | (2.6) | 0.281 | (7.15) | 0.085 | (2.15) | 0.102 | (2.6) |
| 2210 | 0.13 | (3.3) | 0.079 | (2) | 0.146 | (3.7) | 0.13 | (3.3) | 0.091 | (2.3) | 0.146 | (3.7) |
| 2220 | 0.228 | (5.8) | 0.079 | (2) | 0.146 | (3.7) | 0.228 | (5.8) | 0.091 | (2.3) | 0.146 | (3.7) |
| 2225 | 0.281 | (7.15) | 0.079 | (2) | 0.146 | (3.7) | 0.281 | (7.15) | 0.091 | (2.3) | 0.146 | (3.7) |

Large chips above size 2225 are not recommended to be mounted on epoxy board due to thermal expansion coefficient mismatch between ceramic capacitor and epoxy. Where larger sizes are required, it is recommended to use components with ribbon or other adapted leads so as to absorb thermo-mechanical strains.

RECOMMENDED FOOTPRINT FOR SMD CAPACITORS


Ceramic is by nature a material which is sensitive both thermally and mechanically. Stresses caused by the physical and thermal properties of the capacitors, substrates and solders are attenuated by the leads.

Wave soldering is unsuitable for sizes larger than 2220 and for the higher ends of capacitance ranges due to possible thermal shock (capacitance values given upon request).


Infrared and vapor phase reflow, are preferred for high reliability applications as inherent thermo-mechanical strains are lower than those inherent to wave soldering.

Whatever the soldering process is, it is highly recommended to apply a thermal cycle, see hereafter our recommended soldering profile:


RECOMMENDED VAPOR PHASE REFLOW PROFILE



RECOMMENDED IR REFLOW PROFIL



RECOMMENDED WAVE SOLDERING PROFILE



SOLDERING ADVICES FOR IRON SOLDERING

Attachment with a soldering iron is discouraged due to ceramic brittleness and the process control limitations. In the event that a soldering iron must be used, the following precautions should be observed:

- Use a substrate with chip footprints big enough to allow putting side by side one end of the capacitor and the iron tip without any contact between this tip and the component,
- place the capacitor on this footprint,

- heat the substrate until the capacitor's temperature reaches 150°C minimum (preheating step, maximum 1°C per second),
- place the hot iron tip (a flat tip is preferred) on the footprint **without touching the capacitor**. Use a regulated iron with a 30 watts maximum power. The recommended temperature of the iron is 270 ±10°C. The temperature gap between the capacitor and the iron tip must not exceed 120°C,

User Guide

- leave the tip on the footprint for a few seconds in order to increase locally the footprint's temperature,
- use a cored wire solder and put it down on the iron tip. In a preferred way use Sn/Pb/Ag 62/36/2 alloy,
- wait until the solder fillet is formed on the capacitor's termination,
- take away iron and wire solder,
- wait a few minutes so that the substrate and capacitor come back down to

the preheating temperature,

- solder the second termination using the same procedure as the first,
- let the soldered component cool down slowly to avoid any thermal shock.

PACKAGING

TAPE AND REEL

The films used on the reels correspond to standard IEC 60286-3. Films are delivered on reels in compliance with document IEC 286-3 dated 1991.

Minimum quantity is 250 chips.


Maximum quantities per reel are as follows:

- Super 8 reel - Ø 180: 2,500 chips.
- Super 8 reel - Ø 330: 10,000 chips.
- Super 12 reel - Ø 180: 1,000 chips.

Reel marking complies with CECC 32100 standard:

- Model.
- Rated capacitance.
- Capacitance tolerance.
- Rated voltage.
- Batch number.


TRAY PACKAGES



DIMENSIONAL CHARACTERISTICS OF CHIPS TRAY PACKAGES

| Sizes | Nr. of chips/ package | Oriented chips | Dimensions in inches (in mm) | | | | |
|-------|--------------------------|----------------|------------------------------|--------------|--------------|--------------|-----------|
| | | | A | B | C | D | E |
| 0402 | 100 | No | 0.112 (0.302) | | 0.065 (1.65) | 0.167 (4.24) | 2 (50.8) |
| 0403 | 100 | No | 0.112 (0.302) | | 0.065 (1.65) | 0.167 (4.24) | 2 (50.8) |
| 0504 | 100 | Yes | 0.059 (1.5) | 0.045 (1.14) | 0.035 (0.89) | 0.167 (4.24) | 2 (50.8) |
| 0603 | 340 | Yes | 0.1 (2.54) | 0.06 (1.52) | 0.045 (1.14) | 0.167 (4.24) | 2 (50.8) |
| 0805 | 100 | Yes | 0.1 (2.54) | 0.06 (1.52) | 0.045 (1.14) | 0.167 (4.24) | 2 (50.8) |
| 1206 | 100 | No | 0.14 (3.56) | 0.14 (3.56) | 0.06 (1.52) | 0.167 (4.24) | 2 (50.8) |
| 1210 | 100 | Yes | 0.14 (3.56) | 0.14 (3.56) | 0.06 (1.52) | 0.167 (4.24) | 2 (50.8) |
| 1812 | 100 | No | 0.25 (6.35) | 0.25 (6.35) | 0.13 (3.3) | 0.345 (8.76) | 4 (101.6) |
| | 25 | Yes | 0.24 (6.1) | 0.265 (6.73) | 0.07 (1.78) | 0.345 (8.76) | 2 (50.8) |
| 2220 | 100 | Yes | 0.25 (6.35) | 0.25 (6.35) | 0.13 (3.3) | 0.345 (8.76) | 4 (101.6) |
| | 25 | Yes | 0.24 (6.1) | 0.265 (6.73) | 0.07 (1.78) | 0.345 (8.76) | 2 (50.8) |

HIGH Q CAPACITORS TAPE AND REEL PACKAGING SPECIFICATIONS



| Sizes | Type (1) | W±0.3 inches (mm) | F±0.05 inches (mm) | P1±0.1 inches (mm) | T max. inches (mm) | Reel Size inches (mm) | Quantity per Reel |
|----------|----------|----------------------|------------------------|-----------------------|-----------------------|--------------------------|-------------------|
| A (0505) | H | 0,315 (8) | 0,138 (3.5) | 0,157 (4) | 0,010 (0,25) | 7,087 (180) | 3'000 |
| A (0505) | V | 0,315 (8) | 0,138 (3.5) | 0,157 (4) | 0,010 (0,25) | 7,087 (180) | 3'000 |
| S (0603) | H | 0,315 (8) | 0,138 (3.5) | 0,157 (4) | 0,016 (0,4) | 7,087 (180) | 4'000 |
| F (0805) | H | 0,315 (8) | 0,138 (3.5) | 0,157 (4) | 0,016 (0,4) | 7,087 (180) | 4'000 |
| B (1111) | H | 0,315 (8) | 0,138 (3.5) | 0,157 (4) | 0,012 (0,3) | 7,087 (180) | 1'000 |
| B (1111) | V | 0,315 (8) | 0,138 (3.5) | 0,157 (4) | 0,010 (0,25) | 7,087 (180) | 1'000 |
| X (2225) | H | 0,472 (12) | 0,138 (5.5) | 0,472 (12) | 0,018 (0,45) | 12,992 (330) | 500 |
| E (4040) | H | 0,945 (24) | 0,453±0,004 (11,5±0,1) | 0,630 (16) | 0,018 (0,45) | 12,992 (330) | 700 |
| E (4040) | V | 1,260 (32) | 0,559±0,004 (14,2±0,1) | 0,945 (24) | 0,022 (0,55) | 15 (381) | 350 |

(1): Horizontal (H) or Vertical (V) orientation in cavities.

User Guide

EIA STANDARD CAPACITANCE VALUES

Following EIA standard, the values and multiples that are indicated in the chart below can be ordered. E48, E96 series and intermediary values are available upon request.

| E6 (± 20%) | E12 (± 10%) | E24 (± 5%) |
|---------------|----------------|----------------|
| 10 | 10 | 10 11 12 |
| | 12 | 13 |
| | 15 | 15 16 18 |
| 15 | 15 | 18 |
| | 18 | 20 |
| | 22 | 22 24 27 |
| 22 | 22 | 30 |
| | 27 | 33 |
| | 33 | 36 39 43 |
| 33 | 33 | 47 |
| | 39 | 51 |
| | 47 | 56 62 |
| 47 | 47 | 68 |
| | 56 | 75 |
| | 68 | 82 91 |
| 68 | 68 | |
| | 82 | |
| | | |

| Voltage (V) | Code | Letter code |
|-------------|------|-------------|
| 25 | 250 | A |
| 40 | 400 | B |
| 50 | 500 | C |
| 63 | 630 | D |
| 100 | 101 | E |
| 200 | 201 | G |
| 250 | 251 | H |
| 400 | 401 | K |
| 500 | 501 | L |
| 1,000 | 102 | M |
| 2,000 | 202 | P |
| 3,000 | 302 | R |
| 4,000 | 402 | S |
| 5,000 | 502 | T |
| 7,500 | 752 | U |
| 10,000 | 103 | W |

EIA CAPACITANCE CODE

The capacitance is expressed in three digit codes and in units of pico Farads (pF). The first and second digits are significant figures of the capacitance value and the third digit identifies the multiplier.

For capacitance value < 10pF, R designates a decimal point.
See examples below:

| EIA code | Capacitance value | | |
|----------|-------------------|---------|------------|
| | in pF | in nF | in μ F |
| 2R2 | 2.2 | 0.0022 | 0.0000022 |
| 6R8 | 6.8 | 0.0068 | 0.0000068 |
| 220 | 22 | 0.022 | 0.000022 |
| 470 | 47 | 0.047 | 0.000047 |
| 181 | 180 | 0.18 | 0.00018 |
| 221 | 220 | 0.22 | 0.00022 |
| 102 | 1,000 | 1 | 0.001 |
| 272 | 2,700 | 2.7 | 0.0027 |
| 123 | 12,000 | 12 | 0.012 |
| 683 | 68,000 | 68 | 0.068 |
| 124 | 120,000 | 120 | 0.12 |
| 564 | 560,000 | 560 | 0.56 |
| 335 | 3,300,000 | 3,300 | 3.3 |
| 825 | 8,200,000 | 8,200 | 8.2 |
| 156 | 15,000,000 | 15,000 | 15 |
| 686 | 68,000,000 | 68,000 | 68 |
| 107 | 100,000,000 | 100,000 | 100 |
| 227 | 220,000,000 | 220,000 | 220 |

PART MARKING TOLERANCE CODES

Use the following tolerance code chart for part markings:

| Tolerance | Letter code |
|-----------|-------------|
| ±0.25pF | CU |
| ±0.5pF | DU |
| ±1pF | FU |
| ±1% | F |
| ±2% | G |
| ±5% | J |
| ±10% | K |
| ±20% | M |


PART MARKING VOLTAGE CODES

Use the following voltage code chart for part markings:

User Guide

RELIABILITY LEVELS

Exxelia proposes different reliability levels for the ceramic capacitors for both NPO and X7R ceramics.




As the world's leading manufacturer of specific passive components, we stand apart through our ability to quickly evaluate the application specific engineering challenges and provide a cost-effective and efficient solutions.

For requirements that cannot be met by catalog products, we offer leading edge solutions in custom configuration: custom geometries, packaging, characteristics, all is possible thanks to our extensive experience and robust development process, while maintaining the highest level of reliability.

Where necessary, special testing is done to verify requirements, such as low dielectric absorption, ultra-high insulation resistance, low dissipation factor, stability under temperature cycling or under specified environmental conditions, etc.


HIGH CAPACITANCE

- High energy density
- Specific case sizes
- Specific shape of connections (high resistance to vibrations)



HIGH VOLTAGE

- Up to 50 kV
- Specific circular shape




HIGH TEMPERATURE

- Up to 250°C
- Specific shape of connections
- 2,000 hours life time
- HMP soldering



OTHERS

- Screen printed resistors
- Complex components
- Full functions available



General Information

MATERIALS EXPERT

For 50 years and as a market leader, EXXELIA's comprehensive knowledge of the materials properties and performances have enabled us to design capacitors in Porcelain, NPO, BX, 2C1, BP, X7R and $-2200\text{ppm}/^\circ\text{C}$ ceramics.

CUSTOM DESIGNS

Our catalog products don't meet your application?

Based on the valuable experience accumulated over the design of 2,000+ specific ceramic capacitors, you can trust EXXELIA to define a qualitative custom solution in a time effective manner.

NO OBSOLESCENCE

Choosing a standard or custom EXXELIA product means you won't have to worry about obsolescence.

TYPICAL APPLICATIONS

- Aerospace & Defense: cockpit panels, flight control, radio systems, missile guidance systems...
- Space: military and commercial satellites, launcher...
- Medical: MRI, external defibrillators, implantable devices...
- Telecommunications: base stations...
- Oil and gas: drilling tools, MWD, LWD, wellheads...

ISO 9001 AND AS9100C

Quality is at the core of Exxelia's corporate culture. Each sites has its own certifications.

CERTIFICATIONS

Capacitors manufactured by EXXELIA comply with American and European standards and meet the requirements of many international standards. For Space qualified parts (ESA QPL), please refer to our catalog «Ceramic capacitors for Space applications».

QUALITY & RELIABILITY

EXXELIA is committed to design and manufacture high quality and reliability products. The test cycles reproducing the most adverse operating conditions over extended periods (up to 10 000 hours) have logged to date well over 5.10^9 hours/ $^\circ\text{C}$ Component.

Failure rate data can be provided upon request.

CONFLICT MINERALS

EXXELIA is committed to an approach based on «Conflict Minerals Compliance». This US SEC rule demands complete traceability and a control mechanism for the mineral procurement chain, encouraging importers to buy only «certified» ore.

We have discontinued relations with suppliers that procure from the Democratic Republic of the Congo or an adjoining country.

ENVIRONMENT


EXXELIA is committed to applying a robust environmental policy, from product design through to shipment. To control its environmental footprint and reconcile this with the company's functional imperatives, our environmental policy provides for the reduction or elimination of hazardous substances. We also focus on compliance with European Union directives and regulations, notably REACH and RoHS.

RoHS COMPLIANCY

SMD CAPACITORS

The capacitor terminations are generally protected by a nickel barrier formed by electrolytic deposit. This barrier gives chip capacitors leaching performance far exceeding the requirements of all applicable standards. The nickel barrier guarantees a minimum resistance to soldering heat for a period of 1 minute at 260°C in a tin-lead (60/40) or tin-lead-silver (62/36/2) bath without noticeable alteration to the solderability. It also allows repeated soldering-unsoldering and the longer soldering times required by reflow techniques.

However nickel barrier amplifies thermal shock and is not recommended for chip sizes equal or greater than CNC Y (30 30) - [C 282 to C 288 - CNC 80 to CNC 94].



LEADED COMPONENTS

As well as for SMD products, leaded capacitors ranges can also be RoHS. These products, which are characterized by the suffix «W» added to the commercial type, are naturally compatible with the soldering alloys used in RoHS mounting technology. The connections coating is generally an alloy SnAg (with a maximum of 4% Ag). However, on a few products that EXXELIA will precise on request, the coating is pure silver.